



## Task report

# Testing of materials and articles intended to come into contact with food

**Task report 2131b-20/73105-20/68008/1 completely replaces Task report 2131b-20/73105-20/68008, dated 05.10.2020.**

---

Sample description is changed: product code (customer's information) is added.

---

Evidence code: 2131b-20/73105-20/68008/1

Customer: AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV D.O.O.  
LAVA 2 A  
3000 CELJE

Request: Order according to offer no.: PO-213b-30/73105-20/35470 , z dne 21.07.2020

Contractor: Department for Environment and Health Maribor  
Department for Chemical Analysis of Food, Water and Other Environmental Samples  
Maribor

Head of task: Andreja Zorič, univ. dipl. kem.

Sample caretaker: Andreja Zorič, univ. dipl. kem.

Maribor, 16.10.2020

Head of task:

Andreja Zorič, univ. dipl. kem.

Electronically signed Andreja Zorič, univ. dipl. kem. at 16.10.2020 10:24:46

Department for Environment and Health Maribor  
Head of branch:

mag. Emil Žerjal, univ. dipl. inž. kem. tehnol.

The time of the certified signature of deputy and information about the certificate are shown at the top of the first page of the document.

The test report shall not be reproduced except in full without written approval of the department. It should not be used for advertising purposes.

Document authenticity check on: <http://www.nlzoh.si/istovetnost>.



## Sample information

**Sample:** PETG cups intended to come into contact with food  
**Sample number:** 20/68008  
**Purpose:** Analysis on owner request  
**Customer:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV D.O.O., LAVA 2 A, 3000 CELJE  
**Sample taken by:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV D.O.O.  
**Time of sampling:**  
**Place of sampling:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV , LAVA 2A, CELJE  
**Sample received by:** Tatjana Škrabec  
**Place and time of receiving:** Ljubljana, 21.07.2020 08:00

## Sample description

Plastic cups, black or brown colour.

The customer's information about the sample:

-sample material: PETG

-article code:

3D Filament PETG Black, Product code 1.75mm: FG171-9005 (1Kg), FG317-9005 (300g), FG471-9005 (2,1Kg), FG517-9005 (500g);

3D Filament PETG Black, Product code 2.85mm: FG281-9005 (1Kg);

3D Filament PETG Transparent, Product code 1.75mm: FG171-0000 (1Kg), FG517-0000 (500g), FG317-0000 (300g), FG471-0000 (2,1Kg) FG871-0000 (50g);

3D Filament PETG Transparent, Product code 2.85mm: FG281-0000 (1Kg), FG881-0000 (50g)

-purpose of use: contact with food.

## Assessment of the results

*Shown are all results with annexes.*

Parameter	Result	Unit	Norm
<b>Black and brown cups - average sample</b>			
<b>Basic parameters</b>			
Overall migration into 10 vol.% ethanol	<1	mg/dm <sup>2</sup>	10
Overall migration into 3% acetic acid	<1	mg/dm <sup>2</sup>	10
Overall migration into olive oil	<4	mg/dm <sup>2</sup>	10
<b>Black cups</b>			
<b>Elements</b>			
Barium	<0.01	mg/kg	1



#### Elements

Copper	<0.01	mg/kg	5
Zinc	<0.01	mg/kg	5
Cobalt	<0.01	mg/kg	0.05
Manganese	<0.01	mg/kg	0.6
Lithium	<0.01	mg/kg	0.6
Iron	<2	mg/kg	48
Aluminium	<0.05	mg/kg	1
Nickel	<0.01	mg/kg	0.02
Antimony	<0.01	mg/kg	0.04

#### Organic parameters

Acetaldehyde	<1	mg/kg	6
Isophthalic acid	<0.2	mg/kg	5
Terephthalic acid	<0.2	mg/kg	7.5

#### Primary aromatic amines

Aniline	<0.0025	mg/kg	/
m-Phenylenediamine	<0.0025	mg/kg	/
2-naftilamin	<0.0025	mg/kg	/
o-Toluidine	<0.0025	mg/kg	/
4-Chloro-Aniline	<0.0025	mg/kg	/
2-Methoxy aniline	<0.0025	mg/kg	/
6-metoksi m-toluidin (2-Methoxy-5-Methylaniline *)	<0.0025	mg/kg	/
2,4-toluendiamin (Toluene-2,4-diamine *)	<0.0025	mg/kg	/
2,4-Dimetilanilin (2,4-Dimethylaniline *)	<0.0025	mg/kg	/
2,4,5-Trimethylaniline	<0.0025	mg/kg	/
2,6-toluendiamin (2,6-Diaminotoluene *)	<0.0025	mg/kg	/
2,6-Dimethylaniline	<0.0025	mg/kg	/
4,4'-Methylenedi-o-toluidine	<0.0025	mg/kg	/
4-Aminobifenil	<0.0025	mg/kg	/
4-chloro-o-Toluidine	<0.0025	mg/kg	/
4,4'-Thiodianiline	<0.0025	mg/kg	/
4,4'-Methylenedianiline	<0.0025	mg/kg	/
4,4'-Oxydianiline	<0.0025	mg/kg	/
2-Chloroaniline	<0.0025	mg/kg	/

Specific migration limit for primary aromatic amines is 0.01mg/kg of food or food simulant. The limit applies to the sum of primary aromatic amines released from the sample.

#### Brown cups

##### Elements

Barium	<0.01	mg/kg	1
Copper	<0.01	mg/kg	5
Zinc	<0.01	mg/kg	5



**Elements**

Cobalt	<0.01	mg/kg	0.05
Manganese	<0.01	mg/kg	0.6
Lithium	<0.01	mg/kg	0.6
Iron	<2	mg/kg	48
Aluminium	<0.05	mg/kg	1
Nickel	<0.01	mg/kg	0.02
Antimony	<0.01	mg/kg	0.04

**Primary aromatic amines**

Aniline	<0.0025	mg/kg	/
m-Phenylenediamine	<0.0025	mg/kg	/
2-naftilamin	<0.0025	mg/kg	/
o-Toluidine	<0.0025	mg/kg	/
4-Chloro-Aniline	<0.0025	mg/kg	/
2-Methoxy aniline	<0.0025	mg/kg	/
6-metoksi m-toluidin (2-Methoxy-5-Methylaniline *)	<0.0025	mg/kg	/
2,4-toluendiamin (Toluene-2,4-diamine *)	<0.0025	mg/kg	/
2,4-Dimetilanilin (2,4-Dimethylaniline *)	<0.0025	mg/kg	/
2,4,5-Trimethylaniline	<0.0025	mg/kg	/
2,6-toluendiamin (2,6-Diaminotoluene *)	<0.0025	mg/kg	/
2,6-Dimethylaniline	<0.0025	mg/kg	/
4,4'-Methylenedi-o-toluidine	<0.0025	mg/kg	/
4-Aminobifenil	<0.0025	mg/kg	/
4-chloro-o-Toluidine	<0.0025	mg/kg	/
4,4'-Thiodianiline	<0.0025	mg/kg	/
4,4'-Methylenedianiline	<0.0025	mg/kg	/
4,4'-Oxydianiline	<0.0025	mg/kg	/
2-Chloroaniline	<0.0025	mg/kg	/

*Specific migration limit for primary aromatic amines is 0.01 mg/kg of food or food simulant. The limit applies to the sum of primary aromatic amines released from the sample.*

Indications in brackets are identical as in enclosed test reports

**Criterion-Limits according to:**

Regulation (EU) 10/2011 of 14 January 2011, on plastic materials and articles intended to come into contact with food, amended by 321/2011, 1282/2011, 1183/2012, 202/2014, 2015/174, 2016/1416, 2017/752, 2018/79, 2018/213, 2018/831, 2019/37, 2019/988, 2019/1338, 2020/1245), Art.12, Annex I, II





The sample was analysed for overall migration into food simulants 3% acetic acid, 10% ethanol and olive oil and for specific migration of primary aromatic amines, metals (barium, cobalt, copper, iron, lithium, manganese, zinc, aluminium, nickel, antimony), terephthalic acid, isophthalic acid and acetaldehyde into food simulant 3% acetic acid.

Overall and specific migration values from the sample were lower than the quantification limits of the analytical methods used.

With regard to the analysed parameters the sample of PETG cups for food contact (black and brown colour) IS COMPLIANT with:

- art. 10, 11 and 12 of Commission Regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food (with amendments) and
- art. 3, point 1a and b, of Regulation (EC) no. 1935/2004 of the European Parliament and of the Council of 27 October 2004 on materials and articles intended to come into contact with food and repealing Directives 80/590/EEC and 89/109/EEC.

68008\_1.jpg



**Report annexes:**

Testing report with evidence code 2131b-20/73105-20/68008-T/1

Report of chemical analyses with evidence code 1011-20/73105-20/68008-K



# Testing report

Testing report 2131b-20/73105-20/68008-T/1 completely replaces Testing report 2131b-20/73105-20/68008-T, dated 05.10.2020.

Sample description is changed: product code (customer's information) is added.

**Sample:** PETG cups intended to come into contact with food  
**Matrix:** Materials and articles intended to come into contact with food - FCM  
**Sample number:** 20/68008  
**Purpose:** Analysis on owner request  
**Title:** Testing of materials and articles intended to come into contact with food  
**Head of task:** Andreja Zorič, univ. dipl. kem.  
**Customer:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV D.O.O., LAVA 2 A, 3000 CELJE  
**Request:** Order according to offer no.: PO-213b-30/73105-20/35470 , z dne 21.07.2020  
**Place of sampling:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV , LAVA 2A, CELJE  
**Sample status:** The sample complies with criteria for the reception

**Sampling** **Sample receiving** **Issue date:** 16.10.2020  
**Date and hour:** **Date and hour:** 21.07.2020 08:00  
**Taken by:** AZUREFILM PROIZVODNJA 3D **Received by:** Tatjana Škrabec  
TISKALNIKOV IN FILAMENTOV D.O.O.

**Data provided by a customer included in the test report are:**  
sample data, sampling data (the location of the sampling, the date and hour of the sampling, sampler).

## Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result Note	Unit	Expressed as/on	Method Place of execution	Start/End
<b>Black and brown cups - average sample</b>					
<b>Basic parameters</b>					
Migration testing (overall migration)	#			SIST EN 1186-1: 2002, Uredba/Regulation 10/2011, LJ	02.09.20 09.09.20
<i>Migration testing conditions for determination of overall migration into food simulant olive oil:</i> - food simulant: olive oil - time, temperature of contact: 2hours, 70°C (2.9.2020), 4hours, 70°C (9.9.2020), 6hours, 70°C (9.9.2020) - type of contact: total immersion - surface of sample material/volume of simulant: corresponds to the ratio 1dm <sup>2</sup> /100ml. Overall migration was determined in the 3.migration solution.					
Migration testing (overall migration)	#			SIST EN 1186-1: 2002, Uredba/Regulation 10/2011, LJ	14.08.20 14.08.20
<i>Migration testing conditions for determination of overall migration into food simulant 3% acetic acid:</i> - food simulant: 3% acetic acid - time, temperature of contact: 2hours, 70°C, three times repeated - type of contact: article filling - surface of sample material/volume of simulant: 1.71dm <sup>2</sup> /200ml. Overall migration was determined in the 3.migration solution.					



Evidence code:2131b-20/73105-20/68008-T/1

## Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result Note	Unit	Expressed as/on	Method Place of execution	Start/End
<b>Basic parameters</b>					
Migration testing (overall migration)	#			SIST EN 1186-1: 2002, Uredba/Regulation 10/2011, LJ	17.08.20 17.08.20
<i>Migration testing conditions for determination of overall migration into food simulant 10% ethanol:</i> - food simulant: 10% ethanol - time, temperature of contact: 2hours, 70°C, three times repeated - type of contact: article filling - surface of sample material/volume of simulant: 1.71dm <sup>2</sup> /200ml. Overall migration was determined in the 3.migration solution.					
Overall migration into 10 vol.% ethanol	<1	mg/dm <sup>2</sup>		SIST EN 1186-3: 2002, LJ	20.08.20 03.10.20
<i>The reported value is average of measurements on three samples.</i>					
Overall migration into 3% acetic acid	<1	mg/dm <sup>2</sup>		SIST EN 1186-3: 2002, LJ	18.08.20 19.08.20
<i>The reported value is average of measurements on three samples.</i>					
<b>Black cups</b>					
<b>Basic parameters</b>					
Migration testing (specific migration)	#			SIST EN 13130-1: 2004, Uredba/Regulation 10/2011, LJ	18.08.20 18.08.20
<i>Migration testing conditions for determination of primary aromatic amines, metals, terephthalic acid, isophthalic acid and acetaldehyde:</i> - food simulant: 3% acetic acid - time, temperature of contact: 2hours, 70°C, three times repeated - type of contact: article filling - surface of sample material/volume of simulant: 1.71dm <sup>2</sup> /200ml. Specific migration of primary aromatic amines was determined in the 1. migration solution and specific migration of other analytes in the 3.solution.					
<b>Brown cups</b>					
<b>Basic parameters</b>					
Migration testing (specific migration)	#			SIST EN 13130-1: 2004, Uredba/Regulation 10/2011, LJ	18.08.20 18.08.20
<i>Migration testing conditions for determination of primary aromatic amines and metals:</i> - food simulant: 3% acetic acid - time, temperature of contact: 2hours, 70°C, three times repeated - type of contact: article filling - surface of sample material/volume of simulant: 1.71dm <sup>2</sup> /200ml. Specific migration of primary aromatic amines was determined in the 1. migration solution and specific migration of metals in the 3.solution.					

### Locations of analyses:

LJ - OOO Maribor, Grablovičeva ulica 44, Ljubljana



NATIONAL LABORATORY OF  
HEALTH, ENVIRONMENT AND FOOD  
CENTRE FOR ENVIRONMENT AND HEALTH



SLOVENSKA  
AKREDITACIJA

SIST EN ISO/IEC 17025

LP-014

Results marked with # or non-accredited  
relate to not-accredited activity

**Evidence code:**2131b-20/73105-20/68008-T/1

Head of branch:  
mag. Emil Žerjal, univ. dipl. inž. kem. tehnol.

Electronically signed by deputy Alenka Labovič, univ. dipl. inž. kem. tehnol. at 16.10.2020  
11:05:35

Results refer only to the tested sample. The test report shall not be reproduced except in full without written approval of the department. It should not be used for advertising purposes.  
The sample was kept in accordance to the requirements from the time of receipt until the start of the testing. Results apply to the sample as received.  
All additional information on testing is available at the department.





## Report of chemical analyses

**Sample:** PETG cups intended to come into contact with food  
**Matrix:** Materiali in izdelki v stiku z živili - FCM  
**Sample number:** 20/68008  
**Purpose:** Analysis on owner request  
**Title:** Testing of materials and articles intended to come into contact with food  
**Head of task:** Andreja Zorič, univ. dipl. kem.  
**Customer:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV D.O.O., LAVA 2 A, 3000 CELJE  
**Request:** Order according to offer no.: PO-213b-30/73105-20/35470 , z dne 21.07.2020  
**Place of sampling:** AZUREFILM PROIZVODNJA 3D TISKALNIKOV IN FILAMENTOV , LAVA 2A, CELJE  
**Sample status:** The sample complies with criteria for the reception  
**Sampling** **Sample receiving** **Issue date:** 05.10.2020  
**Date and hour:** **Date and hour:** 21.07.2020 08:00  
**Taken by:** AZUREFILM PROIZVODNJA 3D **Received by:** Tatjana Škrabec  
TISKALNIKOV IN FILAMENTOV D.O.O.

**Data provided by a customer included in the test report are:**  
sample data, sampling data (the location of the sampling, the date and hour of the sampling, sampler).

### Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result Note	Unit	Expressed as/on	Method Place of execution	Start/End
<b>Black and brown cups - average sample</b>					
<b>Basic parameters</b>					
Overall migration into olive oil	<4	mg/dm <sup>2</sup>	SIST EN 1186-2:2002 <sup>(1)</sup> , LJ		04.09.20 18.09.20
<i>The reported value is average of measurements on three samples and is calculated as difference between overall migrations from third and second successive migration test. Because of technical reasons the surface of the sample in migration testing was not exactly 1 dm<sup>2</sup>, but the ratio surface to volume of simulant was 1 dm<sup>2</sup>/100ml. The result is corrected for the loss of volatiles. The conditioning of test samples was carried out according to the procedure described in standard EN 1186-2:2002 Annex B</i>					
<b>Black cups</b>					
<b>Elements</b>					
Barium	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Copper	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Zinc	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Cobalt	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Manganese	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Lithium	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20



Evidence code: 1011-20/73105-20/68008-K

## Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result	Note	Unit	Expressed as/on	Method Place of execution	Start/End
Iron	<2.0	#	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Aluminium	<0.050	#	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Nickel	<0.010	#	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Antimony	<0.010	#	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
<b>Organic parameters</b>						
Acetaldehyde	<1	#	mg/kg		ND-IV-NLZOH-OKAMB-127, izdaja 3, MB	16.09.20 17.09.20
Isophthalic acid	<0.2	#	mg/kg		SIST EN 13130-2 modif.: 2004 <sup>[1]</sup> , LJ	28.08.20 28.08.20
Terephthalic acid	<0.2	#	mg/kg		SIST EN 13130-2 modif.: 2004 <sup>[1]</sup> , LJ	28.08.20 28.08.20
<b>Primary aromatic amines</b>						
Aniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
m-Phenylenediamine	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2-naftilamin	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
o-Toluidine	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4-Chloro-Aniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2-Methoxy aniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2-Methoxy-5-Methylaniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
Toluene-2,4-diamine	<0.0025	#	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, izdaja 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2,4-Dimethylaniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2,4,5-Trimethylaniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2,6-Diaminotoluene	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
2,6-Dimethylaniline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4,4'-Methylenedi-o-toluidine	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4-Aminobifenil	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4-chloro-o-Toluidine	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4,4'-Thiodianiline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20
4,4'-Methylenedianiline	<0.0025		mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>[1]</sup> , LJ	20.08.20 21.08.20



Evidence code: 1011-20/73105-20/68008-K

## Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result Note	Unit	Expressed as/on	Method Place of execution	Start/End
4,4'-Oxydianiline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2-Chloroaniline	<0.0025 #	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, izdaja 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
<b>Brown cups</b>					
<b>Elements</b>					
Barium	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Copper	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Zinc	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Cobalt	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Manganese	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Lithium	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Iron	<2.0 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Aluminium	<0.050 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Nickel	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
Antimony	<0.010 #	mg/kg		ISO 17294-2: 2016, modified, MB	20.08.20 21.08.20
<b>Primary aromatic amines</b>					
Aniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
m-Phenylenediamine	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2-naftilamin	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
o-Toluidine	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4-Chloro-Aniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2-Methoxy aniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2-Methoxy-5-Methylaniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
Toluene-2,4-diamine	<0.0025 #	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, izdaja 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2,4-Dimethylaniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2,4,5-Trimethylaniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2,6-Diaminotoluene	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20



Evidence code: 1011-20/73105-20/68008-K

## Analytic results

# Results marked with # refer to not accredited activity

Parameter	Result Note	Unit	Expressed as/on	Method Place of execution	Start/End
2,6-Dimethylaniline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4,4'-Methylenedi-o-toluidine	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4-Aminobifenil	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4-chloro-o-Toluidine	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4,4'-Thiodianiline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4,4'-Methylenedianiline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
4,4'-Oxydianiline	<0.0025	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, ver. 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20
2-Chloroaniline	<0.0025 #	mg/kg		ND-IV-NLZOH-OKAMB-LJ-9 97, izdaja 7 <sup>(1)</sup> , LJ	20.08.20 21.08.20

[1] Parameters were determined in food simulant after migration testing. Migration testing conditions are given in Testing report.

### Locations of analyses:

LJ - OKA Maribor, Grablovičeva ulica 44, Ljubljana

MB - OKA Maribor, Prvomajska ulica 1, Maribor

Head of branch:

dr. Boštjan Križanec, univ. dipl. inž. kem. tehnol.

Electronically signed dr. Boštjan Križanec, univ. dipl. inž. kem. tehnol. at 05.10.2020 07:38:34

Results refer only to the tested sample. The test report shall not be reproduced except in full without written approval of the department. It should not be used for advertising purposes.

The sample was kept in accordance to the requirements from the time of receipt until the start of the testing. Results apply to the sample as received.

All additional information on testing is available at the department.